

QUILL 150

Comfort, Protection and Durability that you always deserved



Wear Your Attitude

TECHNICAL CHARACTERISTICS

Composition	49% FR Viscose, 49% Aramid, 02% Antistatic
Weave	Plain
Weight	150 GSM (±5%)

Parameters	Test Procedure	Warp	Weft
Tensile Strength	EN ISO 13934-1	720 N	480 N
Tear Strength	EN ISO 13937-2	29 N	31 N
Dimensional Stability	EN ISO 6330 – 60°C; Tumble Dry / EN ISO 5077	<3%	<3%

CARE INSTRUCTIONS



Colourfastness	Test Procedure	Result
Against Light	ISO 105 B02	4
Rubbing Dry	ISO 105 X12	4 - 5
Rubbing Wet	ISO 105 X12	3 - 4
Against Perspiration Acid / Basic	ISO 105 E04	4
Washing 60°C	ISO 105 C06	4 - 5
Washing 60°C Staining	ISO 105 C06	4 - 5
Resistance to Pilling	ISO 12945-2- 2000/5000/7000	3-4/ 3/ 3
Abrasion Resistance	ISO 12947-2	>40000
PH	ISO 3071	6.5

Standards	Parameters	Result
 EN ISO 11612	Flame spread: ISO 15025 (Surface Ignition)	A1
	Flame spread: ISO 15025 (Edge Ignition)	A2
	Convective Heat: ISO 9151	B1
	Radiant Heat: ISO 6942	C1
	Contact Heat: ISO 12127	F1
 EN 1149-5	Electrostatic Dissipative Behavior	MET
 NFPA 2112	Protection against Short Duration Thermal Exposure from Fire	PASS