TRANQUIL SWEATER

HARBOR 365
Wear Your Attitude

TECHNICAL CHARACTERISTICS

Composition	60% Modacrylic, 38% Cotton, 02% Antistatic
Weave	Fleece
Weight	350 GSM (±5%)

Parameters	Test Procedure	Results
Bursting Strength	EN ISO 13938-1	259 Kpa
Dimensional Stability	EN ISO 6330-40°C; Line Dry/ Flat Dry	±5%
Heat Shrinkage (180 ±5°C)	ISO 17493:2000	<5%
Color Performance	ISO 105 C06	Grade - 3

CARE INSTRUCTIONS

Standards	Parameters	Results
EN ISO 11612	Flame spread: ISO 15025 (Surface Ignition)	A1
	Flame spread: ISO 15025 (Edge Ignition)	A2
	Convective Heat: ISO 9151	B1
	Radiant Heat: ISO 6942	C2
	Contact Heat: ISO 12127	F2
EN 1149-5	Electrostatic Dissipative Behavior	MET
EN 61482-1-2	Electric Arc Exposure	APC- 1
EN ISO 20471	Hi-Visibility Warning	MET
NFPA 70E	Electric Arc Exposure: ASTM F1959/ ASTM F2621	ATPV Rating- 17 Cal/cm^2